











# ULTRA PRINT

## Liner

### Tehnička specifikacija Technical specification

Grammage Gramatura	Thickness Debljina	Burst Strength Snaga Pritiska	SCT Kompresija	Brightness Belina
$g/m^2$	$\mu m$	$kPa$	$kN/m$	%
<b>210</b>	<b>245</b>	<b>400</b>	<b>2,9</b>	<b>80</b>

	Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
	Belina <b>Brightness</b>	ISO2470	±1%
	Gramatura <b>Grammage</b>	ISO536	±2%
	Debljina <b>Thickness</b>	ISO534	±5%
	Snaga pritiska <b>Burst strength</b>	<b>ISO2759</b>	-10%
	Kompresija <b>SCT</b>	<b>ISO9895</b>	-0.3
	Klima za ispitivanje <b>Testing climate</b>		23±1°C 50±2%°RH
	Reciklabilnost <b>Recyclability</b>	EN13430	in terms of the norm
	Biorazgradljivost <b>Biodegradability</b>	EN13432	in terms of the norm

**Recommended printing methods**  
Preporučeni metod štampe

**Offset, Flexo**  
Ofset štampa, Flexo štampa

**valid from 01.01.2020**