



Specifications

C2S Art Paper / Gloss

Apr. , 2021

Item	Unit	Test Method Reference	80 g/m ²	85 g/m ²	90 g/m ²	100 g/m ²	105 g/m ²	115 g/m ²	120 g/m ²	128 g/m ²	130 g/m ²	150 g/m ²	157 g/m ²
Basis Weight	g/m ²	ISO 536	80±3	85±3	90±3	100±4	105±4	115±4	120±4	128±4	130±4	150±4	157±4
Thickness	μm	T 411	65±4	68±4	72±4	80±4	84±4	92±4	96±4	102±4	104±4	125±4	133±4
Brightness	%	ISO 2470-1	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2
Opacity	%	ISO 2471	89~92	89~92	90~93	92~95	92~95	93~96	94~97	95~98	95~98	96~99	96~99
Roughness	μm	ISO 8791-4	≤1.6	≤1.6	≤1.6	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4
Gloss	%	T 480	65±5	65±5	65±5	65±5	65±5	65±5	65±5	65±5	65±5	65±5	65±5

GOLD EAST PAPER (JIANGSU) CO.,LTD.

Q.A.D.



Specifications

C2S Art Paper /Matt

Apr. , 2021

Item	Unit	Test Method Reference	80 g/m ²	85 g/m ²	90 g/m ²	100 g/m ²	105 g/m ²	115 g/m ²	120 g/m ²	128 g/m ²	130 g/m ²	150 g/m ²	157 g/m ²
Basis Weight	g/m ²	ISO 536	80±3	85±3	90±3	100±4	105±4	115±4	120±4	128±4	130±4	150±4	157±4
Thickness	μm	T 411	72±4	75±4	78±4	84 ±4	90±4	100±4	104±4	110±4	111±4	128±4	140±4
Brightness	%	ISO 2470-1	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2	89±2
Opacity	%	ISO 2471	88~91	89~92	89~92	92~95	92~95	93~96	93~96	94~97	94~97	96~99	96~99
Roughness	μm	ISO 8791-4	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7
Gloss	%	T 480	35±5	35±5	35±5	35±5	35±5	32±5	32±5	32±5	32±5	32±5	32±5

GOLD EAST PAPER (JIANGSU) CO.,LTD.

Q.A.D.

