



# ULTRA PRINT








Brown

Tehnička specifikacija  
Technical specification

Grammage Gramatura	Thickness Debljina	Stiffness <i>Krutost</i> LW5° md	Stiffness <i>Krutost</i> LW5° cd	Stiffness <i>Krutost</i> TABER 15° md	Stiffness <i>Krutost</i> TABER 15° cd
$g/m^2$	$\mu m$	mNm	mNm	mNm	mNm
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
380	495	51,8	20,1	24,7	9,6
400	525	59,6	22,9	28,4	10,9
450	590	77,9	30	37,1	14,3

\*L&W figures are binding, Taber figures are indicative

\*L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni

Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
 Belina <b>Brightness</b>	ISO2470	80±1%
 Gramatura <b>Grammage</b>	ISO536	±2%
 Debljina <b>Thickness</b>	ISO534	±5%
 <i>Krutost</i> <b>Stiffness</b>	DIN53121	-15%
 Klima za ispitivanje <b>Testing climate</b>		23±°C 50±2%°RH
 Reciklabilnost <b>Recyclability</b>	EN13430	in terms of the norm
 Biorazgradljivost <b>Biodegradability</b>	EN13432	in terms of the norm

Recommended printing methods

Preporučeni metod štampe

**Offset, Flexo**

Ofset štampa, Flexo štampa

Valid from 1.4.2023.