



ULTRA PRINT

Teh nic ka s p e c i f i k a c i j a

Technical specification

Color

Grammage Gramatura	Thic kness Debljina	Stiffness md	LW5" cd	Sti ffness md	TA BE R J5" cd
<i>g/m</i>	<i>µm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>
230	285	8,2	4	41	2
250	315	13,5	5,7	6,8	2,9
280	360	19,6	8,1	9,8	4,1
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
380	495	51,8	20,1	24,7	9,6
400	525	59,6	22,9	28,4	10,9
450	590	77,9	30	37,1	14,3

Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
Bel ina Brightness	ISO 2470	80+1%
Grama tura Grammage	ISO 536	+2%
De bljina Thic kness	ISO 54	±5%
Krut osl Sti ff nes s	DIN53121	-15%
Klima za ispit vanje Test ing c li mate		23 °C 50! 2%°RH
Rec ikla bilnos t Recyc labili ty	EN13430	in te rms of the norm
Bior azg ra dlj ivo st Biodegr adability	EN13432	in te rms of the norm

Reccommended printing methods Offset, Flexo
 Preporuceni metod stampe Offset stampa, Flexo stampa
 valid from 01.01.2020