










ULTRA PRINT

Pak

Tehnička specifikacija
Technical specification

| Grammage Gramatura | Thickness Debljina | Stiffness <i>Krutost</i> LW5° md | Stiffness <i>Krutost</i> LW5° cd | Stiffness <i>Krutost</i> TABER 15° md | Stiffness <i>Krutost</i> TABER 15° cd |
|-----------------------|-----------------------|-------------------------------------|-------------------------------------|--|--|
| g/m^2 | μm | mNm | mNm | mNm | mNm |
| 230 | 280 | 8 | 4 | 4 | 2 |
| 250 | 310 | 12,7 | 5 | 6,4 | 2,5 |
| 280 | 355 | 18,4 | 7,4 | 9,2 | 3,7 |
| 300 | 385 | 22,4 | 9,5 | 11,2 | 4,8 |
| 320 | 410 | 27,9 | 11,4 | 14 | 5,7 |
| 350 | 445 | 35,9 | 14,4 | 17,1 | 6,9 |
| 400 | 520 | 51,7 | 20,3 | 24,6 | 9,7 |
| 450 | 585 | 70,3 | 30 | 33,5 | 14,3 |

| Testing Metod Metod Testiranja | Standard Standard | Tolerances Tolerancija |
|--|----------------------|---------------------------|
|  Belina Brightness | ISO2470 | 77±1% |
|  Gramatura Grammage | ISO536 | ±2% |
|  Debljina Thickness | ISO534 | ±5% |
|  Krutost Stiffness | DIN53121 | -15% |
|  Klima za ispitivanje Testing climate | | 23±1°C 50±2%°RH |
|  Reciklabilnost Recyclability | EN13430 | in terms of the norm |
|  Biorazgradljivost Biodegradability | EN13432 | in terms of the norm |

Recommended printing methods

Preporučeni metod štampe

Offset, Flexo

Ofset štampa, Flexo štampa

valid from 01.01.2020