



# ULTRA PRINT

## Tehnikna specifikacija Technical specification

### Special

Grammage Gramalura	Thickness Debljina	Stiffness md	LW5° cd	Stiffness md	TABER 15° cd
g/m	µm	mNm	mNm	mNm	mNm
280	360	19,6	8,1	9,8	4,1
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
400	525	59,6	22,9	28,4	10,9
450	590	77,9	30	37,1	14,3

Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
Belina Brightness	ISO2470	80+1%
Gramatura Grammage	ISO536	+2%
Debljina Thickness	ISO534	±5%
Krutost Stiffness	DIN53121	-15 %
Klimazaispitivanje Testing climate		23+1° C 50 2%° RH
Reciklažnost Recyclability	EN13430	in terms of the norm
Biorazgradljivost Biodegradability	EN13432	in terms of the norm

Recommended printing methods  
Preporučeni metod stampe

Offset, Flexo  
Offset štampa, Flexo štampa

valid from 01.01.2020